

Purification of metallocenes

The present invention relates to a process for purifying  
5 metallocenes, in which a sparingly soluble metallocene halide is  
converted into a readily soluble and readily crystallizable  
metallocene by replacement of at least one halide ligand by an  
alternative negatively charged ligand and the metallocene  
obtained in this way is subsequently purified by crystallization.

10

Metallocenes can, if appropriate in combination with one or more  
cocatalysts, be used as catalyst components for the  
polymerization and copolymerization of olefins. In particular,  
halogen-containing metallocenes are used as catalyst precursors  
15 which can be converted into a polymerization-active cationic  
metallocene complex by means of, for example, an aluminoxane  
(EP-A-129368).

The preparation of metallocenes is known per se (US 4,752,597; US  
20 5,017,714; EP-A-320762; EP-A-416815; EP-A-537686; EP-A- 669340;  
H.H. Brintzinger et al.; Angew. Chem., 107 (1995), 1255; H.H.  
Brintzinger et al., J. Organomet. Chem. 232 (1982), 233). For  
example, cyclopentadienyl-metal compounds can be reacted with  
halides of transition metals such as titanium, zirconium and  
25 hafnium. The metallocene dihalides formed, generally the  
metallocene dichlorides, are, in the case of the industrially  
interesting racemic ansa-bisindenyl-metallocenes which are  
required for the preparation of isotactic polypropylene (EP  
0485823, EP 0549900, EP 0576970, WO 98/40331), generally  
30 sparingly soluble compounds. The crude products formed in the  
syntheses comprise not only the desired metallocenes but also  
considerable amounts of inorganic by-products (e.g. salts),  
organometallic by-products (e.g. isomers) and organic by-products  
(e.g. unreacted substituted cyclopentadienyl ligands). When  
35 metallocenes are used as catalyst components, both in homogeneous  
and in heterogeneous catalyst systems, the by-products adversely  
affect the catalyst activity in olefin polymerization.


For purifying the crude products comprising desired racemic  
40 ansa-bisindenyl-metallocene, methods by means of which inorganic,  
organometallic and organic by-products can be separated from the  
desired metallocene are known. In US 5,455,366 and EP 576970, the  
racemic metallocenes are freed of lithium chloride, the meso  
isomer and organic impurities by extraction with methylene  
45 chloride and subsequent crystallization. In DE 19547247 and DE  
19547248, the crude products from the metallocene synthesis are  
freed of the undesirable by-products by treatment with polar

and/or protic solvents. In US 5,556,997, a metallocene contaminated with tetrahydrofuran-containing by-products is purified further by treatment with tetrahydrofuran.

- 5 Although the major part of the by-products can be separated from the desired racemic metallocene using the known methods, the catalysts prepared using the metallocenes which have been purified in this way, in particular supported catalysts, frequently display unsatisfactory activity, or the proportion of  
10 undesirable low molecular weight polyolefins, known as extractables, is too high. If metallocenes purified by a further recrystallization are used as catalyst components, the abovementioned disadvantages in the polymerization can be avoided. However, large amounts of solvent are required because  
15 of the sparing solubility of the industrially relevant ansa-bisindenyl-metallocene dichlorides. Simple recrystallization of the metallocene dichlorides is thus an uneconomical process step.
- 20 It is an object of the present invention to find an economical purification process by means of which metallocenes of the required quality can be obtained.

We have found that this object is achieved by a simple process in  
25 which the sparingly soluble, insufficiently pure metallocene dihalides are converted into more soluble and readily crystallizable metallocenes by replacement of at least one halide ligand and the new metallocenes prepared in this way are obtained in purified form by removing insoluble constituents by  
30 crystallization.

The present invention accordingly provides a process for purifying compounds of the formula (Ia)



35

40  
70030

45

where

5 M is a metal of transition group III, IV, V or VI of the Periodic Table of the Elements, in particular Ti, Zr or Hf, particularly preferably zirconium,

10 R<sup>1</sup> are identical or different and are each a radical Si(R<sup>12</sup>)<sub>3</sub>, where R<sup>12</sup> are identical or different and are each a hydrogen atom or a C<sub>1</sub>-C<sub>40</sub> group, preferably C<sub>1</sub>-C<sub>20</sub>-alkyl, C<sub>1</sub>-C<sub>10</sub>-fluoroalkyl, C<sub>1</sub>-C<sub>10</sub>-alkoxy, C<sub>6</sub>-C<sub>20</sub>-aryl, C<sub>6</sub>-C<sub>10</sub>-fluoroaryl, C<sub>6</sub>-C<sub>10</sub>-aryloxy, C<sub>2</sub>-C<sub>10</sub>-alkenyl, C<sub>7</sub>-C<sub>40</sub>-arylalkyl, C<sub>7</sub>-C<sub>40</sub>-alkylaryl or C<sub>8</sub>-C<sub>40</sub>-arylalkenyl,

15 or R<sup>1</sup> is a C<sub>1</sub>-C<sub>30</sub> group, preferably C<sub>1</sub>-C<sub>25</sub>-alkyl such as methyl, ethyl, tert-butyl, cyclohexyl or octyl, C<sub>2</sub>-C<sub>25</sub>-alkenyl, C<sub>3</sub>-C<sub>15</sub>-alkylalkenyl, C<sub>6</sub>-C<sub>24</sub>-aryl, C<sub>5</sub>-C<sub>24</sub>-heteroaryl, C<sub>7</sub>-C<sub>30</sub>-arylalkyl, C<sub>7</sub>-C<sub>30</sub>-alkylaryl, fluorinated C<sub>1</sub>-C<sub>25</sub>-alkyl, fluorinated C<sub>6</sub>-C<sub>24</sub>-aryl, fluorinated C<sub>7</sub>-C<sub>30</sub>-arylalkyl, fluorinated C<sub>7</sub>-C<sub>30</sub>-alkylaryl or  
20 C<sub>1</sub>-C<sub>12</sub>-alkoxy,

or two or more radicals R<sup>1</sup> may be joined to one another in such a way that the radicals R<sup>1</sup> and the atoms of the cyclopentadienyl ring which connect them form a C<sub>4</sub>-C<sub>24</sub>-ring  
25 system which may in turn be substituted,

R<sup>2</sup> are identical or different and are each a radical Si(R<sup>12</sup>)<sub>3</sub>, where R<sup>12</sup> are identical or different and are each a hydrogen atom or a C<sub>1</sub>-C<sub>40</sub> group, preferably C<sub>1</sub>-C<sub>20</sub>-alkyl,  
30 C<sub>1</sub>-C<sub>10</sub>-fluoroalkyl, C<sub>1</sub>-C<sub>10</sub>-alkoxy, C<sub>6</sub>-C<sub>14</sub>-aryl, C<sub>6</sub>-C<sub>10</sub>-fluoroaryl, C<sub>6</sub>-C<sub>10</sub>-aryloxy, C<sub>2</sub>-C<sub>10</sub>-alkenyl, C<sub>7</sub>-C<sub>40</sub>-arylalkyl, C<sub>7</sub>-C<sub>40</sub>-alkylaryl or C<sub>8</sub>-C<sub>40</sub>-arylalkenyl,

35 or R<sup>2</sup> is a C<sub>1</sub>-C<sub>30</sub> group, preferably C<sub>1</sub>-C<sub>25</sub>-alkyl such as methyl, ethyl, tert-butyl, cyclohexyl or octyl, C<sub>2</sub>-C<sub>25</sub>-alkenyl, C<sub>3</sub>-C<sub>15</sub>-alkylalkenyl, C<sub>6</sub>-C<sub>24</sub>-aryl, C<sub>5</sub>-C<sub>24</sub>-heteroaryl, C<sub>7</sub>-C<sub>30</sub>-arylalkyl, C<sub>7</sub>-C<sub>30</sub>-alkylaryl, fluorinated C<sub>1</sub>-C<sub>25</sub>-alkyl, fluorinated C<sub>6</sub>-C<sub>24</sub>-aryl, fluorinated C<sub>7</sub>-C<sub>30</sub>-arylalkyl, fluorinated C<sub>7</sub>-C<sub>30</sub>-alkylaryl or  
40 C<sub>1</sub>-C<sub>12</sub>-alkoxy,

or two or more radicals R<sup>2</sup> may be joined to one another in such a way that the radicals R<sup>2</sup> and the atoms of the cyclopentadienyl ring which connect them form a C<sub>4</sub>-C<sub>24</sub> ring  
45 system which may in turn be substituted,

- X is a halogen atom, in particular chlorine,
- n is from 1 to 5 when  $k = 0$ , and n is from 0 to 4 when  $k = 1$ ,
- 5 n' is from 1 to 5 when  $k = 0$ , and n' is from 0 to 4 when  $k = 1$ ,
- m is from 1 to 4, preferably 2,
- k is zero or 1, where the metallocene is unbridged when  $k = 0$
- 10 and is bridged when  $k = 1$ , with preference being given to  $k = 1$ , and

- B is a bridging structural element between the two cyclopentadienyl rings,
- 15 comprising the steps:


- a) reacting the compound of the formula (Ia) with a ligand exchange component
- 20



where

- 25  $M^1$  is a cation or a cationic fragment, in particular Li, Na, K, MgCl, MgBr, MgI, or is an ammonium cation corresponding to an amine,
- 30  $R^3$  is hydrogen or a  $C_1$ - $C_{40}$  group, preferably  $C_1$ - $C_{25}$ -alkyl such as methyl, ethyl, n-propyl, isopropyl tert-butyl, cyclohexyl or octyl,  $C_2$ - $C_{25}$ -alkenyl,  $C_3$ - $C_{15}$ -alkylalkenyl,  $C_6$ - $C_{24}$ -aryl,  $C_5$ - $C_{24}$ -heteroaryl such as pyridyl, furyl or quinolyl,  $C_7$ - $C_{30}$ -arylalkyl,  $C_7$ - $C_{30}$ -alkylaryl, fluorinated  $C_1$ - $C_{25}$ -alkyl, fluorinated  $C_6$ - $C_{24}$ -aryl, fluorinated
- 35  $C_7$ - $C_{30}$ -arylalkyl or fluorinated  $C_7$ - $C_{30}$ -alkylaryl,
- $Y$  is an element of main group 6 of the Periodic Table of the Elements, in particular oxygen or sulfur, or a fragment  $CR^3_2$ ,  $NR^3$ ,  $NR^3(CO)-$ ,  $NR^3(SO_2)-$ ,  $PR^3$ ,  $(=O)R^3$ ,
- 40  $O(CO)-$  or  $O(SO_2)-$ ,

to form the compound of the formula (I)



where



M, R¹, R², R³, X, Y, n, n', m, k, B and R¹² are as defined above and

m' is from 1 to 4, preferably 1 or 2, with the compound of the formula M¹X, where M¹ and X are as defined above, being eliminated, in an inert solvent or solvent mixture,

- b) if desired, separating off solid residues of the formula M¹X
- c) if desired, separating off the inert solvent or solvent mixture,
- d) recrystallizing the compound of the formula (I) from an aprotic hydrocarbon,
- e) separating the compound of the formula (I) from the mother liquor.

In the purification process of the present invention, a metallocene of the formula (Ia) is converted into a metallocene of the formula (I) and subsequently recrystallized.

In the process of the present invention, the compounds of the formulae (Ia) and (I) are



where

M is a metal of transition group III, IV, V or VI of the Periodic Table of the Elements, in particular Ti, Zr or Hf, particularly preferably zirconium,

$R^1$  are identical or different and are each a radical  $Si(R^{12})_3$ , where  $R^{12}$  are identical or different and are each a hydrogen atom or a  $C_1$ - $C_{40}$  group, preferably  $C_1$ - $C_{20}$ -alkyl,  $C_1$ - $C_{10}$ -fluoroalkyl,  $C_1$ - $C_{10}$ -alkoxy,  $C_6$ - $C_{20}$ -aryl,  $C_6$ - $C_{10}$ -fluoroaryl,  $C_6$ - $C_{10}$ -aryloxy,  $C_2$ - $C_{10}$ -alkenyl,  $C_7$ - $C_{40}$ -arylalkyl,  $C_7$ - $C_{40}$ -alkylaryl or  $C_8$ - $C_{40}$ -arylalkenyl,

or  $R^1$  is a  $C_1$ - $C_{30}$  group, preferably  $C_1$ - $C_{25}$ -alkyl such as methyl, ethyl, tert-butyl, cyclohexyl or octyl,  $C_2$ - $C_{25}$ -alkenyl,  $C_3$ - $C_{15}$ -alkylalkenyl,  $C_6$ - $C_{24}$ -aryl,  $C_5$ - $C_{24}$ -heteroaryl,  $C_7$ - $C_{30}$ -arylalkyl,  $C_7$ - $C_{30}$ -alkylaryl, fluorinated  $C_1$ - $C_{25}$ -alkyl, fluorinated  $C_6$ - $C_{24}$ -aryl, fluorinated  $C_7$ - $C_{30}$ -arylalkyl, fluorinated  $C_7$ - $C_{30}$ -alkylaryl or  $C_1$ - $C_{12}$ -alkoxy,

or two or more radicals  $R^1$  may be joined to one another in such a way that the radicals  $R^1$  and the atoms of the cyclopentadienyl ring which connect them form a  $C_4$ - $C_{24}$ -ring system which may in turn be substituted,

$R^2$  are identical or different and are each a radical  $Si(R^{12})_3$ , where  $R^{12}$  are identical or different and are each a hydrogen atom or a  $C_1$ - $C_{40}$  group, preferably  $C_1$ - $C_{20}$ -alkyl,  $C_1$ - $C_{10}$ -fluoroalkyl,  $C_1$ - $C_{10}$ -alkoxy,  $C_6$ - $C_{14}$ -aryl,  $C_6$ - $C_{10}$ -fluoroaryl,  $C_6$ - $C_{10}$ -aryloxy,  $C_2$ - $C_{10}$ -alkenyl,  $C_7$ - $C_{40}$ -arylalkyl,  $C_7$ - $C_{40}$ -alkylaryl or  $C_8$ - $C_{40}$ -arylalkenyl,

or  $R^2$  is a  $C_1$ - $C_{30}$  group, preferably  $C_1$ - $C_{25}$ -alkyl such as methyl, ethyl, tert-butyl, cyclohexyl or octyl,  $C_2$ - $C_{25}$ -alkenyl,  $C_3$ - $C_{15}$ -alkylalkenyl,  $C_6$ - $C_{24}$ -aryl,  $C_5$ - $C_{24}$ -heteroaryl,  $C_7$ - $C_{30}$ -arylalkyl,  $C_7$ - $C_{30}$ -alkylaryl, fluorinated  $C_1$ - $C_{25}$ -alkyl, fluorinated  $C_6$ - $C_{24}$ -aryl, fluorinated  $C_7$ - $C_{30}$ -arylalkyl, fluorinated  $C_7$ - $C_{30}$ -alkylaryl or  $C_1$ - $C_{12}$ -alkoxy,

or two or more radicals  $R^2$  may be joined to one another in such a way that the radicals  $R^2$  and the atoms of the cyclopentadienyl ring which connect them form a  $C_4$ - $C_{24}$  ring system which may in turn be substituted,

- $R^3$  are identical or different and are each hydrogen or a  $C_1$ - $C_{40}$  group, preferably  $C_1$ - $C_{25}$ -alkyl such as methyl, ethyl, n-propyl, isopropyl, tert-butyl, cyclohexyl or octyl,  $C_2$ - $C_{25}$ -alkenyl,  $C_3$ - $C_{15}$ -alkylalkenyl,  $C_6$ - $C_{24}$ -aryl,
- 5  $C_5$ - $C_{24}$ -heteroaryl such as pyridyl, furyl or quinolyl,  $C_7$ - $C_{30}$ -arylalkyl,  $C_7$ - $C_{30}$ -alkylaryl, fluorinated  $C_1$ - $C_{25}$ -alkyl, fluorinated  $C_6$ - $C_{24}$ -aryl, fluorinated  $C_7$ - $C_{30}$ -arylalkyl or fluorinated  $C_7$ - $C_{30}$ -alkylaryl,
- 10 X is a halogen atom, in particular chlorine,
- Y is an element of main group VI of the Periodic Table of the Elements, in particular oxygen or sulfur, or a fragment  $CR^3_2$ ,  $NR^3$ ,  $NR^3(CO)-$ ,  $NR^3(SO_2)-$ ,  $PR^3$ ,  $P(=O)R^3$ ,  $O(CO)-$  or  $O(SO_2)-$ ,
- 15 n is from 1 to 5 when  $k = 0$ , and n is from 0 to 4 when  $k = 1$ ,
- n' is from 1 to 5 when  $k = 0$ , and n' is from 0 to 4 when  $k = 1$ ,
- 20 m is from 1 to 4, preferably 2,
- m' is from 1 to 4, preferably 1 or 2,
- k is zero or 1, where the metallocene is unbridged when  $k=0$  and
- 25 is bridged when  $k=1$ , with preference being given to  $k=1$ , and
- B is a bridging structural element between the two cyclopentadienyl rings.
- 30 Examples of B are  $M^3R^{13}R^{14}$  groups, where  $M^3$  is carbon, silicon, germanium or tin and  $R^{13}$  and  $R^{14}$  are identical or different and are each a  $C_1$ - $C_{20}$ -hydrocarbon-containing group such as  $C_1$ - $C_{10}$ -alkyl,  $C_6$ - $C_{14}$ -aryl or trimethylsilyl. B is preferably  $CH_2$ ,  $CH_2CH_2$ ,  $CH(CH_3)CH_2$ ,  $CH(C_4H_9)C(CH_3)_2$ ,  $C(CH_3)_2$ ,  $(CH_3)_2Si$ ,  $(CH_3)_2Ge$ ,  $(CH_3)_2Sn$ ,
- 35  $(C_6H_5)_2Si$ ,  $(C_6H_5)(CH_3)Si$ ,  $Si(CH_3)(SiR^{20}R^{21}R^{22})$ ,  $(C_6H_5)_2Ge$ ,  $(C_6H_5)_2Sn$ ,  $(CH_2)_4Si$ ,  $CH_2Si(CH_3)_2$ , o- $C_6H_4$  or 2,2'-( $C_6H_4$ ) $_2$ , where  $R^{20}$ ,  $R^{21}$ ,  $R^{22}$  are identical or different and are each a  $C_1$ - $C_{20}$ -hydrocarbon-containing group such as  $C_1$ - $C_{10}$ -alkyl or  $C_6$ - $C_{14}$ -aryl. It is also possible for B together with one or more radicals  $R^1$  and/or  $R^2$  to
- 40 form a monocyclic or polycyclic ring system.


In the purification process of the present invention, metallocene halides of the formula (Ia) are reacted with a ligand exchange component to convert them directly in one reaction step into

45 metallocenes of the formula (I) which, owing to their good

solubility, are obtained in a high space-time yield and in the required purity by crystallization.

Preference is given to a purification process in which a bridged metallocene of the formula (I) is formed from a bridged metallocene of the formula (Ia), in particular a bridged metallocene in which k is 1 and one or both cyclopentadienyl rings are substituted in such a way that they form an indenyl ring. The indenyl ring is preferably substituted, in particular in the 2 position, 4 position, 2,4,5 positions, 2,4,6 positions, 2,4,7 positions or 2,4,5,6 positions, by C<sub>1</sub>-C<sub>20</sub> groups such as C<sub>1</sub>-C<sub>18</sub>-alkyl or C<sub>6</sub>-C<sub>18</sub>-aryl, where two or more substituents of the indenyl ring may also together form a ring system.

Particular preference is given to a purification process in which a bridged metallocene of the formula (IIa) is converted into a bridged metallocene of the formula (II),



where

M is Ti, Zr or Hf, particularly preferably zirconium,

R<sup>3</sup> are identical or different and are each hydrogen or a C<sub>1</sub>-C<sub>30</sub> group, preferably C<sub>1</sub>-C<sub>10</sub>-alkyl such as methyl, ethyl, n-propyl, isopropyl, tert-butyl, cyclohexyl or octyl, C<sub>2</sub>-C<sub>16</sub>-alkenyl, C<sub>6</sub>-C<sub>24</sub>-aryl, C<sub>5</sub>-C<sub>24</sub>-heteroaryl such as pyridyl, furyl or quinolyl, C<sub>7</sub>-C<sub>30</sub>-arylalkyl, C<sub>7</sub>-C<sub>30</sub>-alkylaryl, fluorinated C<sub>6</sub>-C<sub>24</sub>-aryl, fluorinated C<sub>7</sub>-C<sub>30</sub>-arylalkyl or fluorinated C<sub>7</sub>-C<sub>30</sub>-alkylaryl,

R<sup>4</sup>, R<sup>6</sup> are identical or different and are each a hydrogen atom or a C<sub>1</sub>-C<sub>20</sub> group, preferably C<sub>1</sub>-C<sub>18</sub>-alkyl such as methyl, ethyl, n-butyl, cyclohexyl or octyl, C<sub>2</sub>-C<sub>10</sub>-alkenyl, C<sub>3</sub>-C<sub>15</sub>-alkylalkenyl, C<sub>6</sub>-C<sub>18</sub>-aryl, C<sub>5</sub>-C<sub>18</sub>-heteroaryl such as pyridyl, furyl or quinolyl, C<sub>7</sub>-C<sub>20</sub>-arylalkyl, C<sub>7</sub>-C<sub>20</sub>-alkylaryl, fluorinated C<sub>1</sub>-C<sub>12</sub>-alkyl, fluorinated



C<sub>6</sub>-C<sub>18</sub>-aryl, fluorinated C<sub>7</sub>-C<sub>20</sub>-arylalkyl or fluorinated C<sub>7</sub>-C<sub>20</sub>-alkylaryl,

5 R<sup>5</sup>, R<sup>7</sup> are identical or different and are each a hydrogen atom or a C<sub>1</sub>-C<sub>20</sub> group, preferably C<sub>1</sub>-C<sub>18</sub>-alkyl such as methyl, ethyl, n-butyl, cyclohexyl or octyl, C<sub>2</sub>-C<sub>10</sub>-alkenyl, C<sub>3</sub>-C<sub>15</sub>-alkylalkenyl, C<sub>6</sub>-C<sub>18</sub>-aryl, C<sub>5</sub>-C<sub>18</sub>-heteroaryl such as pyridyl, furyl or quinolyl, C<sub>7</sub>-C<sub>20</sub>-arylalkyl, C<sub>7</sub>-C<sub>20</sub>-alkylaryl, fluorinated C<sub>1</sub>-C<sub>12</sub>-alkyl, fluorinated C<sub>6</sub>-C<sub>18</sub>-aryl, fluorinated C<sub>7</sub>-C<sub>20</sub>-arylalkyl or fluorinated C<sub>7</sub>-C<sub>20</sub>-alkylaryl,

15 R<sup>8</sup> and R<sup>9</sup> are identical or different and are each a hydrogen atom, a halogen atom or a C<sub>1</sub>-C<sub>20</sub> group, preferably a linear or branched C<sub>1</sub>-C<sub>18</sub>-alkyl group such as methyl, ethyl, tert-butyl, cyclohexyl or octyl, C<sub>2</sub>-C<sub>10</sub>-alkenyl, C<sub>3</sub>-C<sub>15</sub>-alkylalkenyl, a C<sub>6</sub>-C<sub>18</sub>-aryl group which may be substituted, in particular phenyl, tolyl, xylyl, tert-butylphenyl, ethylphenyl, di-tert-butylphenyl, naphthyl, acenaphthyl, phenanthrenyl or anthracenyl, C<sub>5</sub>-C<sub>18</sub>-heteroaryl such as pyridyl, furyl or quinolyl, C<sub>7</sub>-C<sub>20</sub>-arylalkyl, C<sub>7</sub>-C<sub>20</sub>-alkylaryl, fluorinated C<sub>1</sub>-C<sub>12</sub>-alkyl, fluorinated C<sub>6</sub>-C<sub>18</sub>-aryl, fluorinated C<sub>7</sub>-C<sub>20</sub>-arylalkyl or fluorinated C<sub>7</sub>-C<sub>20</sub>-alkylaryl, and two  
20 radicals R<sup>8</sup> or R<sup>9</sup> may form a monocyclic or polycyclic ring system which may in turn be substituted,

25 X is a halogen atom, in particular chlorine,

30 Y is an element of main group VI of the Periodic Table of the Elements, in particular oxygen or sulfur, or a fragment CR<sup>3</sup><sub>2</sub>, NR<sup>3</sup>, NR<sup>3</sup>(CO)-, NR<sup>3</sup>(SO<sub>2</sub>)-, PR<sup>3</sup>, P(=O)R<sup>3</sup>, O(CO)- or O(SO<sub>2</sub>)-,

35 l, l' are identical or different and are each an integer from zero to 4, preferably 1 or 2, particularly preferably 1,

m' is 1 or 2,

40 B is a bridging structural element between the two indenyl radicals.

Examples of B are M<sup>3</sup>R<sup>13</sup>R<sup>14</sup> groups, where M<sup>3</sup> is carbon, silicon, germanium or tin, preferably carbon or silicon, and R<sup>13</sup> and R<sup>14</sup>  
45 are identical or different and are each hydrogen or a C<sub>1</sub>-C<sub>20</sub>-hydrocarbon-containing group such as C<sub>1</sub>-C<sub>10</sub>-alkyl, C<sub>6</sub>-C<sub>14</sub>-aryl or trimethylsilyl. B is preferably CH<sub>2</sub>, CH<sub>2</sub>CH<sub>2</sub>,

## 10

CH(CH<sub>3</sub>)CH<sub>2</sub>, CH(C<sub>4</sub>H<sub>9</sub>)C(CH<sub>3</sub>)<sub>2</sub>, C(CH<sub>3</sub>)<sub>2</sub>, (CH<sub>3</sub>)<sub>2</sub>Si, (CH<sub>3</sub>)<sub>2</sub>Ge, (CH<sub>3</sub>)<sub>2</sub>Sn, (C<sub>6</sub>H<sub>5</sub>)<sub>2</sub>C, (C<sub>6</sub>H<sub>5</sub>)<sub>2</sub>Si, (C<sub>6</sub>H<sub>5</sub>)(CH<sub>3</sub>)Si, Si(CH<sub>3</sub>)(SiR<sup>20</sup>R<sup>21</sup>R<sup>22</sup>), (C<sub>6</sub>H<sub>5</sub>)<sub>2</sub>Ge, (C<sub>6</sub>H<sub>5</sub>)<sub>2</sub>Sn, (CH<sub>2</sub>)<sub>4</sub>Si, CH<sub>2</sub>Si(CH<sub>3</sub>)<sub>2</sub>, o-C<sub>6</sub>H<sub>4</sub> or 2,2'-(C<sub>6</sub>H<sub>4</sub>)<sub>2</sub>, where R<sup>20</sup>, R<sup>21</sup>, R<sup>22</sup> are identical or different and are each a

- 5 C<sub>1</sub>-C<sub>20</sub>-hydrocarbon-containing group such as C<sub>1</sub>-C<sub>10</sub>-alkyl or C<sub>6</sub>-C<sub>14</sub>-aryl.

Very particular preference is given to a purification process in which a bridged metallocene of the formula (IIa) is converted  
10 into a bridged metallocene of the formula (II), where

M is zirconium,

- 15 R<sup>3</sup> are identical or different and are each hydrogen or a C<sub>1</sub>-C<sub>30</sub> group, preferably C<sub>1</sub>-C<sub>10</sub>-alkyl such as methyl, ethyl, n-propyl, isopropyl, tert-butyl, cyclohexyl or octyl, C<sub>2</sub>-C<sub>12</sub>-alkenyl, C<sub>6</sub>-C<sub>24</sub>-aryl, C<sub>5</sub>-C<sub>24</sub>-heteroaryl such as pyridyl, furyl or quinolyl, C<sub>7</sub>-C<sub>30</sub>-arylalkyl, C<sub>7</sub>-C<sub>30</sub>-alkylaryl, fluorinated C<sub>6</sub>-C<sub>24</sub>-aryl, fluorinated  
20 C<sub>7</sub>-C<sub>30</sub>-arylalkyl or fluorinated C<sub>7</sub>-C<sub>30</sub>-alkylaryl,

- R<sup>4</sup>, R<sup>6</sup> are identical or different and are each a hydrogen atom or a C<sub>1</sub>-C<sub>12</sub>-alkyl group, preferably an alkyl group such as methyl, ethyl, n-butyl or octyl, particularly  
25 preferably methyl or ethyl,

R<sup>5</sup>, R<sup>7</sup> are hydrogen atoms,

- 30 R<sup>8</sup> and R<sup>9</sup> are identical or different and are each a hydrogen atom, a halogen atom or a C<sub>1</sub>-C<sub>20</sub> group, preferably a linear or branched C<sub>1</sub>-C<sub>8</sub>-alkyl group such as methyl, ethyl, tert-butyl, cyclohexyl or octyl, C<sub>2</sub>-C<sub>6</sub>-alkenyl, C<sub>3</sub>-C<sub>6</sub>-alkylalkenyl, a C<sub>6</sub>-C<sub>18</sub>-aryl group which may be substituted, in particular phenyl, tolyl, xylyl, tert-butylphenyl, ethylphenyl, di-tert-butylphenyl, naphthyl, acenaphthyl, phenanthrenyl or anthracenyl, C<sub>5</sub>-C<sub>18</sub>-heteroaryl such as pyridyl, furyl or quinolyl, C<sub>7</sub>-C<sub>12</sub>-arylalkyl, C<sub>7</sub>-C<sub>12</sub>-alkylaryl, fluorinated  
35 C<sub>1</sub>-C<sub>8</sub>-alkyl, fluorinated C<sub>6</sub>-C<sub>18</sub>-aryl, fluorinated C<sub>7</sub>-C<sub>12</sub>-arylalkyl or fluorinated C<sub>7</sub>-C<sub>12</sub>-alkylaryl,  
40

X is chlorine,

## 11

- Y is an element of main group VI of the Periodic Table of the Elements, in particular oxygen or sulfur, or a fragment  $\text{CR}^3_2$ ,  $\text{NR}^3$ ,  $\text{NR}^3(\text{CO})-$ ,  $\text{NR}^3(\text{SO}_2)-$ ,  $\text{PR}^3$ ,  $\text{P}(=\text{O})\text{R}^3$ ,  $\text{O}(\text{CO})-$  or  $\text{O}(\text{SO}_2)-$ ,
- 5 1, 1' are identical or different and are each an integer from zero to 4, preferably 1 or 2, particularly preferably 1,
- m' is 1 or 2, preferably 1, and
- 10 B is a bridging structural element between the two indenyl radicals and is preferably  $(\text{CH}_3)_2\text{Si}$ ,  $(\text{CH}_3)_2\text{Ge}$ ,  $(\text{C}_6\text{H}_5)_2\text{Si}$ ,  $(\text{C}_6\text{H}_5)(\text{CH}_3)\text{Si}$ ,  $\text{CH}_2\text{CH}_2$ ,  $\text{CH}(\text{CH}_3)\text{CH}_2$ ,  $\text{CH}(\text{C}_4\text{H}_9)\text{C}(\text{CH}_3)_2$ ,  $\text{CH}_2$ ,  $\text{C}(\text{CH}_3)_2$ ,  $(\text{C}_6\text{H}_5)_2\text{C}$ , particularly preferably  $(\text{CH}_3)_2\text{Si}$ ,  $\text{CH}_2$  and  $\text{CH}_2\text{CH}_2$ .
- 15

When Y = oxygen and  $\text{R}^3$  is alkenyl, individual  $\text{CH}_2$  units in the alkenyl radical can be replaced by  $\text{C}=\text{O}$ ,  $\text{C}(\text{O})\text{O}$  or  $\text{C}(\text{O})\text{NR}^3$ .



- 20 The metallocenes of the formulae I and II obtained in the purification process of the present invention display a significantly better solubility in inert organic solvents than do the corresponding metalloces of the formulae (Ia) and (IIa). For the purposes of the present invention, a significantly better
- 25 solubility means that the molar concentrations in organic solvents are at least doubled, preferably more than quadrupled and very particularly preferably increased by a factor of more than eight.
- 30 As inert organic solvents for metallocenes, use is made of the usual aliphatic or aromatic hydrocarbons and also halogen-containing, oxygen-containing or nitrogen-containing hydrocarbons. Nonlimiting examples of the individual classes of solvent are heptane, toluene, dichlorobenzene, methylene
- 35 chloride, tetrahydrofuran or triethylamine.

The purification process of the present invention is preferably carried out using metallocenes of the formulae (Ia) and (IIa), i.e. racemic metallocene dichlorides as are mentioned in

- 40 EP-A-0485823, EP-A-0549900, EP-A-0576970, WO 98/22486 and WO 98/40331. These are hereby incorporated by reference into the present description.

- However, it is also possible to use any mixtures of the racemic
- 45 metallocene dichloride of the formula (IIIa) with the corresponding meso-metallocene dichloride of the formula (IIIb),

where the symbols and indices are defined as under formula (IIa),  
in the purification process of the present invention.



The metallocenes of the formulae (Ia) and (IIa) used in the  
purification process of the present invention, preferably the  
20 metallocenes of the formula (IIa), can be used in the form in  
which they are obtained directly from the metallocene synthesis  
together with the inorganic, organometallic and organic  
by-products, or in the form in which they can be obtained after  
separating off a large part of the by-products by one of the  
25 abovementioned known purification methods.

Illustrative but nonlimiting examples of metallocenes of the  
formula (Ia) or (IIa) which can be used in the purification  
process of the present invention are:

- 30 dimethylsilanediylbis(indenyl)zirconium dichloride  
dimethylsilanediylbis(2-methylindenyl)zirconium dichloride  
methylidenebis(2-methylindenyl)zirconium dichloride  
isopropylidenebis(2-methylindenyl)zirconium dichloride  
35 dimethylsilanediylbis(2-methylbenzoindenyl)zirconium dichloride  
dimethylsilanediylbis(4-naphthylindenyl)zirconium dichloride  
dimethylsilanediylbis(2-methyl-4-(1-naphthyl)indenyl)zirconium  
dichloride  
methylidenebis(2-methyl-4-(1-naphthyl)indenyl)zirconium  
40 dichloride  
isopropylidenebis(2-methyl-4-(1-naphthyl)indenyl)zirconium  
dichloride  
dimethylsilanediylbis(2-methyl-4-(2-naphthyl)indenyl)zirconium  
dichloride  
45 dimethylsilanediylbis(2-methyl-4-phenylindenyl)zirconium  
dichloride  
methylidenebis(2-methyl-4-phenylindenyl)zirconium dichloride

- isopropylidenebis(2-methyl-4-phenylindenyl)zirconium dichloride  
dimethylsilanediylbis(2-methyl-4-t-butylindenyl)zirconium  
dichloride  
dimethylsilanediylbis(2-methyl-4-isopropylindenyl)zirconium  
5 dichloride  
dimethylsilanediylbis(2-methyl-4-ethylindenyl)zirconium  
dichloride  
dimethylsilanediylbis(2,4-dimethylindenyl)zirconium dichloride  
dimethylsilanediylbis(2-ethylindenyl)zirconium dichloride  
10 dimethylsilanediylbis(2-ethyl-4-ethylindenyl)zirconium dichloride  
dimethylsilanediylbis(2-ethyl-4-phenylindenyl)zirconium  
dichloride  
dimethylsilanediylbis(2-methyl-4,5-benzoindenyl)zirconium  
dichloride  
15 methylidenebis(2-methyl-4,5-benzoindenyl)zirconium dichloride  
isopropylidenebis(2-methyl-4,5-benzoindenyl)zirconium dichloride  
dimethylsilanediylbis(2-methyl-4,6-diisopropylindenyl)zirconium  
dichloride  
dimethylsilanediylbis(2-methyl-4,5-diisopropylindenyl)zirconium  
20 dichloride  
dimethylsilanediylbis(2,4,6-trimethylindenyl)zirconium dichloride  
dimethylsilanediylbis(2,5,6-trimethylindenyl)zirconium dichloride  
dimethylsilanediylbis(2,4,7-trimethylindenyl)zirconium dichloride  
dimethylsilanediylbis(2-methyl-5-isobutylindenyl)zirconium  
25 dichloride  
dimethylsilanediylbis(2-methyl-5-t-butylindenyl)zirconium  
dichloride  
methyl(phenyl)silanediylbis(2-methyl-4-phenylindenyl)zirconium  
dichloride  
30 methyl(phenyl)silanediylbis(2-methyl-4,6-diisopropylindenyl)-  
zirconium dichloride  
methyl(phenyl)silanediylbis(2-methyl-4-isopropylindenyl)zirconium  
dichloride  
methyl(phenyl)silanediylbis(2-methyl-4,5-benzoindenyl)zirconium  
35 dichloride  
methyl(phenyl)silanediylbis(2-methylindenyl)zirconium dichloride  
methyl(phenyl)silanediylbis(2-methyl-5-isobutylindenyl)zirconium  
dichloride  
1,2-ethanediylbis(2-methyl-4-phenylindenyl)zirconium dichloride  
40 1,4-butanediylbis(2-methyl-4-phenylindenyl)zirconium dichloride  
1,2-ethanediylbis(2-methyl-4,6-diisopropylindenyl)zirconium  
dichloride  
1,4-butanediylbis(2-methyl-4-isopropylindenyl)zirconium  
dichloride  
45 1,4-butanediylbis(2-methyl-4,5-benzoindenyl)zirconium dichloride  
1,2-ethanediylbis(2-methyl-4,5-benzoindenyl)zirconium dichloride  
1,2-ethanediylbis(2,4,7-trimethylindenyl)zirconium dichloride

- 1,2-ethanediylbis(2-methylindenyl)zirconium dichloride  
 1,4-butanediylbis(2-methylindenyl)zirconium dichloride  
 [4-( $\eta^5$ -cyclopentadienyl)-4,6,6-trimethyl( $\eta^5$ -4,5-tetrahydropentalene)]zirconium dichloride  
 5 [4-( $\eta^5$ -3'-trimethylsilylcyclopentadienyl)-4,6,6-trimethyl( $\eta^5$ -4,5-tetrahydropentalene)]zirconium dichloride  
 [4-( $\eta^5$ -3'-isopropylcyclopentadienyl)-4,6,6-trimethyl-( $\eta^5$ -4,5-tetrahydropentalene)]zirconium dichloride  
 [4-( $\eta^5$ -cyclopentadienyl)-4,7,7-trimethyl-( $\eta^5$ -4,5,6,7-tetrahydroindenyl)]zirconium dichloride  
 10 [4-( $\eta^5$ -3'-tert-butylcyclopentadienyl)-4,7,7-trimethyl( $\eta^5$ -4,5,6,7-tetrahydroindenyl)]zirconium dichloride  
 4-( $\eta^5$ -3'-methylcyclopentadienyl)-4,7,7-trimethyl-( $\eta^5$ -4,5,6,7-tetrahydroindenyl)]zirconium dichloride  
 15 4-( $\eta^5$ -3'-trimethylsilylcyclopentadienyl)-2-trimethylsilyl-4,7,7-trimethyl-( $\eta^5$ -4,5,6,7-tetrahydroindenyl)]zirconium dichloride  
 dimethylsilanediylbis(tetrahydroindenyl)zirconium dichloride  
 isopropylidenebisindenylzirconium dichloride  
 isopropylidenecyclopentadienyl-9-fluorenylzirconium dichloride  
 20 isopropylidenecyclopentadienylindenylzirconium dichloride  
 diphenylmethylidene(cyclopentadienyl)-(9-fluorenyl)zirconium dichloride  
 diphenylmethylidene(3-methylcyclopentadienyl)-(9-fluorenyl)-zirconium dichloride  
 25 diphenylmethylidene(3-isopropylcyclopentadienyl)-(9-fluorenyl)-zirconium dichloride  
 diphenylmethylidene(3-tert-butylcyclopentadienyl)-(9-fluorenyl)-zirconium dichloride  
 dimethylsilanediylcyclopentadienyl-9-fluorenylzirconium  
 30 dichloride  
 diphenylsilanediylcyclopentadienyl-9-fluorenylzirconium dichloride  
 dimethylsilanediylbis(2-methyl-4-(tert-butylphenylindenyl)-zirconium dichloride  
 35 dimethylsilanediylbis(2-methyl-4-(4-trifluoromethylphenylindenyl)zirconium dichloride  
 dimethylsilanediylbis(2-methyl-4-(4-methoxyphenylindenyl)-zirconium dichloride  
 dimethylsilanediylbis(2-ethyl-4-(4-methylphenylindenyl)zirconium  
 40 dichloride  
 dimethylsilanediylbis(2-ethyl-4-(4-ethylphenylindenyl)zirconium dichloride  
 dimethylsilanediylbis(2-ethyl-4-(4-trifluormethylphenylindenyl)-zirconium dichloride  
 45 dimethylsilanediylbis(2-ethyl-4-(4-methoxyphenylindenyl)zirconium dichloride

- dimethylsilanediylbis(2-methyl-4-(4'-tert-butylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-methyl-4-(3',5'-di-tert-butylphenyl)-  
indenyl)zirconium dichloride
- 5 methylidenebis(2-methyl-4-(4'-tert-butylphenyl)indenyl)zirconium  
dichloride  
isopropylidenebis(2-methyl-4-(4'-tert-butylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-methyl-4-(4'-methylphenyl)indenyl)-
- 10 zirconium dichloride  
dimethylsilanediylbis(2-methyl-4-(4'-ethylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-methyl-4-(4'-n-propylphenyl)indenyl)-  
zirconium dichloride
- 15 dimethylsilanediylbis(2-methyl-4-(4'-isopropylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-methyl-4-(4'-n-butylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-methyl-4-(4'-hexylphenyl)indenyl)-
- 20 zirconium dichloride  
dimethylsilanediylbis(2-methyl-4-(4'-sec-butylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-ethyl-4-phenyl)indenyl)zirconium  
dichloride
- 25 dimethylsilanediylbis(2-ethyl-4-(4'-methylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-ethyl-4-(4'-ethylphenyl)indenyl)zirconium  
dichloride  
dimethylsilanediylbis(2-ethyl-4-(4'-n-propylphenyl)indenyl)-
- 30 zirconium dichloride  
dimethylsilanediylbis(2-ethyl-4-(4'-isopropylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-ethyl-4-(4'-n-butylphenyl)indenyl)-  
zirconium dichloride
- 35 dimethylsilanediylbis(2-ethyl-4-(4'-hexylphenyl)indenyl)zirconium  
dichloride  
dimethylsilanediylbis(2-ethyl-4-(4'-pentylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-ethyl-4-(4'-cyclohexylphenyl)indenyl)-
- 40 zirconium dichloride  
dimethylsilanediylbis(2-ethyl-4-(4'-sec-butylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)-  
zirconium dichloride
- 45 dimethylsilanediylbis(2-ethyl-4-(3',5'-di-tert-butylphenyl)-  
indenyl)zirconium dichloride

- methylidenebis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)zirconium dichloride  
isopropylidenebis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)-zirconium dichloride
- 5 dimethylsilanediylbis(2-n-propyl-4-phenyl)indenyl)zirconium dichloride  
dimethylsilanediylbis(2-n-propyl-4-(4'-methylphenyl)indenyl)-zirconium dichloride  
dimethylsilanediylbis(2-n-propyl-4-(4'-ethylphenyl)indenyl)-zirconium dichloride
- 10 dimethylsilanediylbis(2-n-propyl-4-(4'-n-propylphenyl)indenyl)-zirconium dichloride  
dimethylsilanediylbis(2-n-propyl-4-(4'-isopropylphenyl)indenyl)-zirconium dichloride
- 15 dimethylsilanediylbis(2-n-propyl-4-(4'-n-butylphenyl)indenyl)-zirconium dichloride  
dimethylsilanediylbis(2-n-propyl-4-(4'-hexylphenyl)indenyl)-zirconium dichloride  
dimethylsilanediylbis(2-n-propyl-4-(4'-cyclohexylphenyl)indenyl)-zirconium dichloride
- 20 dimethylsilanediylbis(2-n-propyl-4-(4'-sec-butylphenyl)indenyl)-zirconium dichloride  
dimethylsilanediylbis(2-n-propyl-4-(4'-tert-butylphenyl)indenyl)-zirconium dichloride
- 25 dimethylsilanediylbis(2-n-propyl-4-(3',5'-di-tert-butylphenyl)indenyl)zirconium dichloride  
methylidenebis(2-n-propyl-4-(4'-tert-butylphenyl)indenyl)-zirconium dichloride  
isopropylidenebis(2-n-propyl-4-(4'-tert-butylphenyl)indenyl)-zirconium dichloride
- 30 dimethylsilanediylbis(2-n-butyl-4-phenyl)indenyl)zirconium dichloride  
dimethylsilanediylbis(2-n-butyl-4-(4'-methylphenyl)indenyl)-zirconium dichloride
- 35 dimethylsilanediylbis(2-n-butyl-4-(4'-ethylphenyl)indenyl)-zirconium dichloride  
dimethylsilanediylbis(2-n-butyl-4-(4'-n-propylphenyl)indenyl)-zirconium dichloride  
dimethylsilanediylbis(2-n-butyl-4-(4'-isopropylphenyl)indenyl)-zirconium dichloride
- 40 dimethylsilanediylbis(2-n-butyl-4-(4'-n-butylphenyl)indenyl)-zirconium dichloride  
dimethylsilanediylbis(2-n-butyl-4-(4'-hexylphenyl)indenyl)-zirconium dichloride
- 45 dimethylsilanediylbis(2-n-butyl-4-(4'-cyclohexylphenyl)indenyl)-zirconium dichloride




- dimethylsilanediylbis(2-n-butyl-4-(4'-sec-butylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-n-butyl-4-(4'-tert-butylphenyl)indenyl)-  
zirconium dichloride  
5 dimethylsilanediylbis(2-hexyl-4-phenyl)indenyl)zirconium  
dichloride  
dimethylsilanediylbis(2-hexyl-4-(4'-methylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-hexyl-4-(4'-ethylphenyl)indenyl)zirconium  
10 dichloride  
dimethylsilanediylbis(2-hexyl-4-(4'-n-propyl-phenyl)-indenyl)-  
zirconium dichloride  
Dimethylsilanediylbis(2-hexyl-4-(4'-isopropylphenyl)indenyl)-  
zirconium dichloride  
15 dimethylsilanediylbis(2-hexyl-4-(4'-n-butylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-hexyl-4-(4'-hexylphenyl)indenyl)zirconium  
dichloride  
dimethylsilanediylbis(2-hexyl-4-(4'-cyclohexylphenyl)indenyl)-  
20 zirconium dichloride  
dimethylsilanediylbis(2-hexyl-4-(4'-sec-butylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediylbis(2-hexyl-4-(4'-tert-butylphenyl)indenyl)-  
zirconium dichloride  
25 dimethylgermandiylbis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)-  
zirconium dichloride  
dimethylgermandiylbis(2-methyl-4-(4'-tert-butylphenyl)indenyl)-  
zirconium dichloride  
ethylidenebis(2-ethyl-4-phenyl)indenyl)zirconium dichloride  
30 ethylidenebis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)zirconium  
dichloride  
ethylidenebis(2-n-propyl-4-(4'-tert-butylphenyl)indenyl)zirconium  
dichloride  
ethylidenebis(2-methyl-4-(4'-tert-butylphenyl)indenyl)zirconium  
35 dichloride  
methylethylidenebis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)-  
zirconium dichloride  
dimethylsilanediyl(2-methylazapentalene)(2-methylindenyl)-  
zirconium dichloride  
40 dimethylsilanediyl(2-methylazapentalene)(2-methyl-  
4-phenylindenyl)zirconium dichloride  
dimethylsilanediyl(2-methylazapentalene)(2-methyl-  
4,5-benzoindenyl)zirconium dichloride  
dimethylsilanediyl(2-methylazapentalene)(2-ethyl-  
4-(4'-tert-butylphenylindenyl)zirconium dichloride  
45 dimethylsilanediyl(2-methylazapentalene)(2-methyl-  
4-(4'-tert-butylphenyl)indenyl)zirconium dichloride

- dimethylsilanediyl(2-methylazapentalene)(2-n-propyl-4-(4'-tert-butylphenyl)indenyl)zirconium dichloride  
 dimethylsilanediyl(2-ethylazapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride  
 5 dimethylsilanediyl(2-ethylazapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride  
 dimethylsilanediyl(2-ethylazapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride  
 dimethylsilanediyl(2-ethylazapentalene)(2-ethyl-4-(4'-tert-butylphenyl)indenyl)zirconium dichloride  
 10 dimethylsilanediyl(2-ethylazapentalene)(2-methyl-4-(4'-tert-butylphenyl)indenyl)zirconium dichloride  
 Dimethylsilanediyl(2-ethylazapentalene)(2-n-propyl-4-(4'-tert-butylphenyl)indenyl)zirconium dichloride  
 15 dimethylsilanediyl(2-methylthiapentalene)(2-methylindenyl)-zirconium dichloride  
 dimethylsilanediyl(2-methylthiapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride  
 dimethylsilanediyl(2-methylthiapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride  
 20 dimethylsilanediyl(2-methylthiapentalene)(2-ethyl-4-(4'-tert-butylphenyl)indenyl)zirconium dichloride  
 dimethylsilanediyl(2-methylthiapentalene)(2-n-propyl-4-(4'-tert-butylphenyl)indenyl)zirconium dichloride  
 25 dimethylsilanediyl(2-ethylthiapentalene)(2-methylindenyl)-zirconium dichloride  
 dimethylsilanediyl(2-ethylthiapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride  
 dimethylsilanediyl(2-ethylthiapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride  
 30 dimethylsilanediyl(2-ethylthiapentalene)(2-ethyl-4-(4'-tert-butylphenyl)indenyl)zirconium dichloride  
 dimethylsilanediyl(2-ethylthiapentalene)(2-n-propyl-4-(4'-tert-butylphenyl)indenyl)zirconium dichloride

35

In the purification process of the present invention, at least one metallocene halide of the formula (Ia) or (IIa) is reacted with at least one ligand exchange component  $M^1YR^3$ , forming the metallocenes of the formula (I) or (II). Here, the ligand

- 40 exchange component serves to introduce the ligand  $Y-R^3$ . The metallocenes of the formula (I) and (II) can, owing to their good solubility, be obtained in the required quality and in good space-time yields by crystallization. The salts formed in the ligand exchange can, for example, be removed by known filtration  
 45 techniques.



## 20

The compound  $M^1-Y-R^3$  used in the purification process of the present invention can be prepared, for example, by deprotonation of the acid compound  $H-Y-R^3$  using a suitable base, for example butyllithium, methyllithium, sodium hydride, potassium hydride, 5 sodium, potassium, Grignard compounds or amines, in an inert solvent or solvent mixture, or  $M^1-Y-R^3$  is a commercially available organometallic compound such as an organolithium compound, for example methyllithium, an organoaluminum compound, for example trimethylaluminum, or a Grignard compound, for example 10 benzylmagnesium chloride.

Nonlimiting examples of suitable solvents are hydrocarbons which may be halogenated, e.g. benzene, toluene, xylene, mesitylene, ethylbenzene, chlorobenzene, dichlorobenzene, fluorobenzene, 15 decalin, tetralin, pentane, hexane, cyclohexane, ethers such as diethyl ether, di-n-butyl ether, tert-butyl methyl ether (MTBE), tetrahydrofuran (THF), 1,2-dimethoxyethane (DME), anisole, triglyme, dioxane, amides such as dimethylformamide (DMF), dimethylacetamide, N-methyl-2-pyrrolidinone (NMP), sulfoxides 20 such as dimethyl sulfoxide (DMSO), phosphoramides such as hexamethylphosphoramide, urea derivatives such as 1,3-dimethyltetrahydro-2(1H)-pyrimidinone, ketones such as acetone, ethyl methyl ketone, esters such as ethyl acetate, nitriles such as acetonitrile and also any mixtures of these. 25 Preference is given to solvents or solvent mixtures in which the subsequent reaction with the metallocene dichloride can likewise be carried out. Nonlimiting examples of such solvents are toluene, hexane, heptane, xylene, tetrahydrofuran (THF), dimethoxyethane (DME), toluene/THF, heptane/DME and toluene/DME.

30 The compounds of the type  $H-Y-R^3$  are, for example, alcohols, phenols, carboxylic acids, alkylsulfonic and arylsulfonic acids, primary and secondary amines, primary and secondary anilines, carboxamides, sulfonamides, dialkylphosphines or diarylphosphines 35 and dialkylphosphine oxides or diarylphosphine oxides. Examples of  $CH$ -acid, enolisable compounds  $H-Y-R^3$  are malonic esters, cyanoacetic esters, acetoacetic esters, 1,3-diketones, enolisable esters and enolisable ketones.

40 Compounds of the type  $H-Y-R^3$  preferably contain only one functional group  $H-Y$  and the radical  $R^3$  is as defined above.

Illustrative but nonlimiting examples of compounds of the formula  $H-Y-R^3$  which can be used according to the present invention are: 45

## 21

- 2,4-di-tert-butylphenol; 2,6-di-tert-butylphenol;  
 3,5-di-tert-butylphenol; 2,6-di-sec-butylphenol;  
 2,4-dimethylphenol; 2,3-dimethylphenol; 2,5-dimethylphenol;  
 2,6-dimethylphenol; 3,4-dimethylphenol; 3,5-dimethylphenol;  
 5 phenol; 2-methylphenol; 3-methylphenol; 4-methylphenol;  
 2-ethylphenol; 3-ethylphenol; 4-ethylphenol; 2-sec-butylphenol;  
 2-tert-butylphenol; 3-tert-butylphenol; 4-sec-butylphenol;  
 4-tert-butylphenol; 2-isopropyl-5-methylphenol;  
 4-isopropyl-3-methylphenol; 5-isopropyl-2-methylphenol;  
 10 5-isopropyl-3-methylphenol; 2,4-bis(2-methyl-2-butyl)phenol;  
 2,6-di-tert-butyl-4-methylphenol; 4-nonylphenol;  
  
 2-isopropylphenol; 3-isopropylphenol; 4-isopropylphenol;  
 2-propylphenol; 4-propylphenol; 2,3,5-trimethylphenol;  
 15 2,3,6-trimethylphenol; 2,4,6-trimethylphenol;  
 3,4,5-trimethylphenol; 2-tert-butyl-4-methylphenol;  
 2-tert-butyl-5-methylphenol; 2-tert-butyl-6-methylphenol;  
 4-(2-methyl-2-butyl)phenol; 2-tert-butyl-4-ethylphenol;  
 2,6-diisopropylphenol; 4-octylphenol;  
 20 4-(1,1,3,3-tetramethylbutyl)phenol;  
 2,6-di-tert-butyl-4-ethylphenol;  
 4-sec-butyl-2,6-di-tert-butylphenol; 4-dodecylphenol;  
 2,4,6-tri-tert-butylphenol; 3-(pentadecyl)phenol;  
 2-methyl-1-naphthol;  
 25  
 1-naphthol; 2-naphthol; 1-acenaphthenol; 2-hydroxybiphenyl;  
 3-hydroxybiphenyl; 4-hydroxybiphenyl; hydroxypyridines;  
 hydroxyquinolines; 2-hydroxycarbazole; hydroxyquinaldines;  
 8-hydroxyquinazoline; 2-hydroxyquinoxaline;  
 30 2-hydroxydibenzofuran; 2-hydroxydiphenylmethane,  
 1-hydroxyisoquinolines, 5,6,7,8-tetrahydro-1-naphthol; methanol;  
 ethanol; propanol; isopropanol; butanol; tert-butanol;  
 isobutanol; 2-butanol; hexanol; cyclohexanol; octadecanol; benzyl  
 alcohol; 2-methylbenzyl alcohol; 3-methylbenzyl alcohol;  
 35 4-methylbenzyl alcohol; aniline; N-methylaniline; o-toluidine;  
 2,3-dimethylaniline; 2,4-dimethylaniline; 2,5-dimethylaniline;  
 2,6-dimethylaniline; N-ethylaniline; 2-ethylaniline;  
 N-ethyl-o-toluidine; N-ethyl-m-toluidine; 2-isopropylaniline;  
 2-propylaniline; 2,4,6-trimethylaniline; 2-tert-butylaniline;  
 40 2,3-dimethyl-N-ethylaniline; isopropylamine; tert-butylamine;  
 diethylamine; N-methylisopropylamine; N-ethylisopropylamine;  
 diisopropylamine; N-methyl-tert-butylamine; N-benzylmethylamine;  
 2-methylbenzylamine; 3-methylbenzylamine; 4-methylbenzylamine;  
 1-phenylethylamine; 2-phenylethylamine; acetic acid; propionic  
 45 acid; butyric acid; phenylacetic acid; benzoic acid; toluic acid;  
 dimethylbenzoic acid; 4-tert-butylbenzoic acid; methanesulfonic  
 acid; trifluoromethanesulfonic acid; p-toluenesulfonic acid;

N-methylacetamide; N-methylpropionamide; benzamide; diphenylphosphine; dimethyl malonate; diethyl malonate; dimethyl methylmalonate; diethyl methylmalonate; diethyl ethylmalonate; methyl acetoacetate; ethyl acetoacetate; ethyl  
5 2-ethylacetoacetate; 1,3-pentanedione; dibenzoylmethane; methyl phenylacetate; methyl isobutyrate; acetophenone; tert-butyl methyl ketone and phenylacetone.

The molar ratio of reagent  $M^1-Y-R^3$  to the metallocene halide, in  
10 particular the metallocene dichloride (e.g. of the formula III) is generally in the range from 5 : 1 to 0.8 : 1, preferably from 2.5 : 1 to 0.9 : 1.

The concentration of metallocene dichloride (e.g. of the formula  
15 IIa) or of reagent  $M^1-Y-R^3$  in the reaction mixture is generally in the range from 0.001 mol/l to 8 mol/l, preferably from 0.01 to 3 mol/l, particularly preferably from 0.05 mol/l to 2 mol/l.

The reaction time for the reaction of the metallocene dichloride  
20 (e.g. of the formula IIa) with the reagent  $M^1-Y-R^3$  is generally in the range from 5 minutes to 1 week, preferably from 15 minutes to 48 hours.

After conversion of the metallocenes of the formulae (Ia) and  
25 (IIa) into the metallocenes of the formulae (I) and (II), insoluble constituents such as the salts or metal oxyhalides formed are preferably separated off before the new metallocenes are crystallized. For this purpose, preference is given to filtering and extracting a solution or suspension of the new  
30 metallocenes in the inert solvent or solvent mixture which has been used in the ligand exchange reaction. The recrystallization is preferably carried out in aprotic hydrocarbons, in particular polar aprotic hydrocarbons. Particular preference is given to toluene, hexane, heptane, xylene, tetrahydrofuran (THF),  
35 dimethoxyethane (DME), toluene/THF, heptane/DME or toluene/DME.

The solvent or solvent mixture used in the extraction is at a temperature in the range from 20°C to the boiling point of the solvent or solvent mixture. The extraction is preferably carried  
40 out at 0-20°C below the boiling point.

The resulting solution of the new metallocene is possibly concentrated by evaporation and the new metallocene subsequently crystallizes out.

The crystallization is carried out at from  $-78^{\circ}\text{C}$  to  $200^{\circ}\text{C}$ , preferably from  $-30^{\circ}\text{C}$  to  $110^{\circ}\text{C}$ , particularly preferably from  $-15^{\circ}\text{C}$  to  $30^{\circ}\text{C}$ .

- 5 The purified metallocene obtained by crystallization can in turn be isolated from the mother liquor by filtration techniques.

The process of the present invention enables at least twice as much metallocene to be purified in existing apparatuses as was possible hitherto. In preferred embodiments, this factor is substantially exceeded, so that costly capacity expansions can be avoided.

The metallocenes of the formulae I and II obtainable by the purification process of the present invention are highly active catalyst components for olefin polymerization. Depending on the substitution pattern of the ligands, the metallocenes can be obtained as an isomer mixture. For the polymerization, the metallocenes are preferably used as pure isomers.

- 20 Preference is given to using the pseudo-rac metallocenes of the formula II.

The metallocenes of the formulae I and II obtainable by the purification process of the present invention are particularly suitable as constituents of catalyst systems for preparing polyolefins by polymerization of at least one olefin in the presence of a catalyst comprising at least one cocatalyst and at least one metallocene. For the purposes of the present invention, the term polymerization encompasses both homopolymerization and copolymerization.

The metallocenes of the formulae I and II, in particular of the formula II, obtainable by the purification process of the present invention can be used for the polymerization of one or more olefins of the formula  $\text{R}^{\alpha}\text{-CH=CH-R}^{\beta}$ , where  $\text{R}^{\alpha}$  and  $\text{R}^{\beta}$  are identical or different and are each a hydrogen atom or a hydrocarbon radical having from 1 to 20 carbon atoms, in particular from 1 to 10 carbon atoms, and  $\text{R}^{\alpha}$  and  $\text{R}^{\beta}$  together with the atoms connecting them may form one or more rings. Examples of such olefins are 1-olefins having 2 - 40, preferably from 2 to 10, carbon atoms, e.g. ethene, propene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene or 1-octene, styrene, dienes such as 1,3-butadiene, 1,4-hexadiene, vinylnorbornene, norbornadiene, ethylnorbornadiene and cyclic olefins such as norbornene, tetracyclododecene or methylnorbornene. Preference is given to homopolymerizing ethylene or propylene or copolymerizing ethylene

with one or more cyclic olefins such as norbornene and/or one or more dienes having from 4 to 20 carbon atoms, e.g. 1,3-butadiene or 1,4-hexadiene. Examples of such copolymers are ethylene-norbornene copolymers, ethylene-propylene copolymers and  
5 ethylene-propylene-1,4-hexadiene copolymers.

The metallocenes of the formulae I and II obtained in the purification process of the present invention display olefin polymerization activities which are at least equal to and  
10 sometimes superior to those of the dihalide compounds, and the polyolefins obtained display a reduction in the proportion of undesirable low molecular weight extractables.

The polymerization is carried out at from - 60 to 300 °C ,  
15 preferably from 50 to 200 °C, very particularly preferably from 50 - 80 °C. The pressure is from 0.5 to 2000 bar, preferably from 5 to 64 bar.

The polymerization can be carried out in solution, in bulk, in  
20 suspension or in the gas phase, continuously or batchwise, in one or more stages. Preferred embodiments are gas-phase and bulk polymerization.

The catalyst used preferably comprises one of the metallocene  
25 compounds obtainable by the purification process of the present invention. It is also possible to use mixtures of two or more metallocene compounds, e.g. for preparing polyolefins having a broad or multimodal molar mass distribution.


30 The cocatalyst, which together with a metallocene of the formula I or II obtainable by the purification process of the present invention forms the catalyst system, comprises at least one compound such as an aluminoxane or a Lewis acid or an ionic compound which reacts with a metallocene to convert it into a  
35 cationic compound.

As aluminoxane, preference is given to using a compound of the formula (VII)


40  $(R AlO)_n$  (VII).

Further suitable aluminoxanes may be, for example, cyclic as in formula (VI)






5 or linear as in formula (IV)



15 or of the cluster type as in formula (V)



30 Such aluminoxanes are described, for example, in JACS 117 (1995), 6465-74, Organometallics 13 (1994), 2957-2969.

The radicals R in the formulae (IV), (V), (VI) and (VII) may be identical or different and may each be a C<sub>1</sub>-C<sub>20</sub>-hydrocarbon group  
 35 such as a C<sub>1</sub>-C<sub>6</sub>-alkyl group, a C<sub>6</sub>-C<sub>18</sub>-aryl group or benzyl, or hydrogen, and p is an integer from 2 to 50, preferably from 10 to 35.

The radicals R are preferably identical and are each methyl,  
 40 isobutyl, n-butyl, phenyl or benzyl, particularly preferably methyl.

If the radicals R are different, they are preferably methyl and hydrogen, methyl and isobutyl or methyl and n-butyl, with  
 45 hydrogen or isobutyl or n-butyl preferably being present in an amount of 0.01 - 40% (number of radicals R).

26

The aluminoxane can be prepared in various ways by known methods. One of the methods is, for example, reacting an aluminum-hydrocarbon compound and/or a hydridoaluminum-hydrocarbon compound with water (gaseous, solid, liquid or bound - for example as water of crystallization) in an inert solvent (e.g. toluene).

To prepare an aluminoxane having different alkyl groups R, two different trialkylaluminums ( $AlR_3 + AlR'_3$ ) corresponding to the desired composition and reactivity are reacted with water (cf. S. Pasynkiewicz, Polyhedron 9 (1990) 429 and EP-A-0,302,424).

Regardless of the method of preparation, all aluminoxane solutions have a variable content of unreacted aluminum starting compound which is present in free form or as adduct.

As Lewis acid, preference is given to using at least one organoboron or organoaluminum compound containing  $C_1$ - $C_{20}$  groups such as branched or unbranched alkyl or haloalkyl, e.g. methyl, propyl, isopropyl, isobutyl, trifluoromethyl, unsaturated groups such as aryl or haloaryl, e.g. phenyl, tolyl, benzyl, p-fluorophenyl, 3,5-difluorophenyl, pentachlorophenyl, pentafluorophenyl, 3,4,5-trifluorophenyl and 3,5-di(trifluoromethyl)phenyl.

Examples of Lewis acids are trimethylaluminum, triethylaluminum, triisobutylaluminum, tributylaluminum, trifluoroborane, triphenylborane, tris(4-fluorophenyl)borane, tris(3,5-difluorophenyl)borane, tris(4-fluoromethylphenyl)borane, tris(pentafluorophenyl)borane, tris(tolyl)borane, tris(3,5-dimethylphenyl)borane, tris(3,5-difluorophenyl)borane,  $[(C_6F_5)_2BO]_2Al-Me$ ,  $[(C_6F_5)_2BO]_3Al$  and/or tris(3,4,5-trifluorophenyl)borane. Particular preference is given to tris(pentafluorophenyl)borane.

As ionic cocatalysts, preference is given to using compounds containing a noncoordinating anion, for example tetrakis(pentafluorophenyl)borates, tetraphenylborates,  $SbF_6^-$ ,  $CF_3SO_3^-$  or  $ClO_4^-$ . As cationic counterion, use is made of protonated Lewis bases such as methylamine, aniline, dimethylamine, diethylamine, N-methylaniline, diphenylamine, N,N-dimethylaniline, trimethylamine, triethylamine, tri-n-butylamine, methyldiphenylamine, pyridine, p-bromo-N,N-dimethylaniline, p-nitro-N,N-dimethylaniline, triethylphosphine, triphenylphosphine, diphenylphosphine, tetrahydrothiophene or triphenylcarbenium.

Examples of such ionic compounds are

- triethylammonium tetra(phenyl)borate,
  - tributylammonium tetra(phenyl)borate,
  - 5 trimethylammonium tetra(tolyl)borate,
  - tributylammonium tetra(tolyl)borate,
  - tributylammonium tetra(pentafluorophenyl)borate,
  - tributylammonium tetra(pentafluorophenyl)aluminate,
  - tripropylammonium tetra(dimethylphenyl)borate,
  - 10 tributylammonium tetra(trifluoromethylphenyl)borate,
  - tributylammonium tetra(4-fluorophenyl)borate,
  - N,N-dimethylanilinium tetra(phenyl)borate,
  - N,N-diethylanilinium tetra(phenyl)borate,
  - N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate,
  - 15 N,N-dimethylanilinium tetrakis(pentafluorophenyl)aluminate,
  - di(propyl)ammonium tetrakis(pentafluorophenyl)borate,
  - di(cyclohexyl)ammonium tetrakis(pentafluorophenyl)borate,
  - triphenylphosphonium tetrakis(phenyl)borate,
  - triethylphosphonium tetrakis(phenyl)borate,
  - 20 diphenylphosphonium tetrakis(phenyl)borate,
  - tri(methylphenyl)phosphonium tetrakis(phenyl)borate,
  - tri(dimethylphenyl)phosphonium tetrakis(phenyl)borate,
  - triphenylcarbenium tetrakis(pentafluorophenyl)borate,
  - triphenylcarbenium tetrakis(pentafluorophenyl)aluminate,
  - 25 triphenylcarbenium tetrakis(phenyl)aluminate,
  - ferrocenium tetrakis(pentafluorophenyl)borate and/or
  - ferrocenium tetrakis(pentafluorophenyl)aluminate.
- Preference is given to triphenylcarbenium  
tetrakis(pentafluorophenyl)borate and/or
- 30 N,N-dimethylanilinium tetrakis(pentafluorophenyl)borate.

It is also possible to use mixtures of at least one Lewis acid and at least one ionic compound.

- 35 Further suitable cocatalyst components are borane or carborane compounds such as

- 7,8-dicarbaundecaborane(13),
- undecahydrido-7,8-dimethyl-7,8-dicarbaundecaborane,
- 40 dodecahydrido-1-phenyl-1,3-dicarbanonaborane,
- tri(butyl)ammonium undecahydrido-8-ethyl-7,9-dicarbaundecaborate,
- 4-carbanonaborane(14),
- bis(tri(butyl)ammonium) nonaborate,
- bis(tri(butyl)ammonium) undecaborate,
- 45 bis(tri(butyl)ammonium) dodecaborate,
- bis(tri(butyl)ammonium) decachlorodecaborate,
- tri(butyl)ammonium 1-carbadecaborate,

- tri(butyl)ammonium 1-carbadodecaborate,  
 tri(butyl)ammonium 1-trimethylsilyl-1-carbadecaborate,  
 tri(butyl)ammonium  
 bis(nonahydrido-1,3-dicarbanonaborato)cobaltate(III),  
 5 tri(butyl)ammonium  
 bis(undecahydrido-7,8-dicarbaundecaborato)ferrate(III).

- Further cocatalysts which can be used in unsupported or supported form are the compounds specified in EP-A-0924223, DE-A-19622207,  
 10 EP-A-0601830, EP-A-0824112, EP-A-0824113, WO 99/06414, EP-A-0811627 and DE-A-19804970.

- The support component of the catalyst system of the present invention may be any organic or inorganic, inert solid, in  
 15 particular a porous support such as talc, inorganic oxides and finely divided polymer powders (e.g. polyolefins).

- Suitable inorganic oxides may be found among the oxides of elements of groups 2,3,4,5,13,14,15 and 16 of the Periodic Table  
 20 of the Elements. Examples of oxides preferred as supports include silicon dioxide, aluminum oxide and also mixed oxides of the two elements and corresponding oxide mixtures. Other inorganic oxides which can be used alone or in combination with the abovementioned preferred oxidic supports are, for example, MgO, ZrO<sub>2</sub>, TiO<sub>2</sub> or  
 25 B<sub>2</sub>O<sub>3</sub>, to name only a few.

- The support materials used have a specific surface area in the range from 10 to 1000 m<sup>2</sup>/g, a pore volume in the range from 0.1 to 5 ml/g and a mean particle size of from 1 to 500 µm. Preference  
 30 is given to supports having a specific surface area in the range from 50 to 500 m<sup>2</sup>/g, a pore volume in the range from 0.5 to 3.5 ml/g and a mean particle size in the range from 5 to 350 µm. Particular preference is given to supports having a specific surface area in the range from 200 to 400 m<sup>2</sup>/g, a pore volume in  
 35 the range from 0.8 to 3.0 ml/g and a mean particle size of from 10 to 200 µm.

- If the support material used naturally has a low moisture content or residual solvent content, dehydration or drying before use can  
 40 be omitted. If this is not the case, for example when using silica gel as support material, dehydration or drying is advisable. Thermal dehydration or drying of the support material can be carried out under reduced pressure with simultaneous inert gas blanketing (e.g. nitrogen). The drying temperature is in the  
 45 range from 100 to 1000 °C, preferably from 200 to 800 °C. The parameter pressure is not critical in this case. The duration of the drying process can be from 1 to 24 hours. Shorter or longer

drying times are possible, provided that equilibrium with the hydroxyl groups on the support surface can be established under the conditions chosen, which normally takes from 4 to 8 hours.

- 5 Dehydration or drying of the support material can also be carried out by chemical means, by reacting the adsorbed water and the hydroxyl groups on the surface with suitable passivating agents. Reaction with the passivating reagent enables all or some of the hydroxyl groups to be converted into a form which leads to no
- 10 adverse interaction with the catalytically active centers. Suitable passivating agents are, for example, silicon halides and silanes, e.g. silicon tetrachloride, chlorotrimethylsilane, dimethylaminotrichlorosilane, or organometallic compounds of aluminum, boron and magnesium, for example trimethylaluminum,
- 15 triethylaluminum, triisobutylaluminum, triethylborane, dibutylmagnesium. Chemical dehydration or passivation of the support material is carried out, for example, by reacting a suspension of the support material in a suitable solvent with the passivating reagent in pure form or as a solution in a suitable
- 20 solvent in the absence of air and moisture. Suitable solvents are, for example, aliphatic or aromatic hydrocarbons such as pentane, hexane, heptane, toluene or xylene. Passivation is carried out at from 25 °C to 120 °C, preferably from 50 to 70 °C. Higher and lower temperatures are possible. The reaction time is
- 25 from 30 minutes to 20 hours, preferably from 1 to 5 hours. After chemical dehydration is complete, the support material is isolated by filtration under inert conditions, washed one or more times with suitable inert solvents as have been described above and subsequently dried in a stream of inert gas or under reduced
- 30 pressure.

- Organic support materials such as finely divided polyolefin powders (e.g. polyethylene, polypropylene or polystyrene) can also be used and should likewise be freed of adhering moisture,
- 35 solvent residues or other impurities by means of appropriate purification and drying operations before use.

- The catalyst system is prepared by mixing at least one metallocene as rac-meso isomer mixture, at least one cocatalyst
- 40 and at least one passivated support.

- To prepare the supported catalyst system, at least one of the above-described metallocene components obtainable by the purification process of the present invention is brought into
- 45 contact with at least one cocatalyst component in a suitable solvent, preferably giving a soluble reaction product, an adduct or a mixture.

## 30

The composition obtained in this way is then mixed with the dehydrated or passivated support material, the solvent is removed and the resulting supported metallocene catalyst system is dried to ensure that all or most of the solvent is removed from the pores of the support material. The supported catalyst is obtained as a free-flowing powder.

A process for preparing a free-flowing and possibly prepolymerized supported catalyst system comprises the following steps:

- a) preparing a metallocene/cocatalyst mixture in a suitable solvent or suspension medium, where the metallocene component is obtainable from the purification process of the present invention and has one of the above-described structures;
  - b) applying the metallocene/cocatalyst mixture to a porous, preferably inorganic dehydrated support;
  - c) removing the major part of the solvent from the resulting mixture;
  - d) isolating the supported catalyst system;
  - e) if desired, prepolymerizing the supported catalyst system obtained using one or more olefinic monomer(s) to give a prepolymerized supported catalyst system.
- Preferred solvents for preparing the metallocene/cocatalyst mixture are hydrocarbons and hydrocarbon mixtures which are liquid at the chosen reaction temperature and in which the individual components preferably dissolve. However, solubility of the individual components is not a prerequisite as long as it is ensured that the reaction product of metallocene and cocatalyst components is soluble in the solvent selected. Examples of suitable solvents include alkanes such as pentane, isopentane, hexane, heptane, octane and nonane; cycloalkanes such as cyclopentane and cyclohexane; and aromatics such as benzene, toluene, ethylbenzene and diethylbenzene. Very particular preference is given to toluene.

The amounts of aluminoxane and metallocene used in the preparation of the supported catalyst system can be varied over a wide range. Preference is given to a molar ratio of aluminum to transition metal in the metallocene of from 10 : 1 to 1000 : 1, very particularly preferably from 50 : 1 to 500 : 1.

In the case of methylaluminoxane, preference is given to using 30% strength toluene solutions; however, the use of 10% strength solutions is also possible.

## 31

For preactivation, the solid metallocene is dissolved in a solution of the aluminoxane in a suitable solvent. It is also possible to dissolve the metallocene separately in a suitable solvent and subsequently to combine this solution with the  
5 aluminoxane solution. Preference is given to using toluene.

The preactivation time is from 1 minute to 200 hours.

The preactivation can take place at room temperature (25 °C). The  
10 use of higher temperatures can in some cases shorten the preactivation time required and result in an additional increase in the activity. In this case, higher temperature means a range from 50 to 100 °C.

15 The preactivated solution or metallocene/cocatalyst mixture is subsequently combined with an inert support material, usually silica gel, in the form of a dry powder or as a suspension in one of the abovementioned solvents. The support material is preferably used as a powder. The order of addition is immaterial.

20 The preactivated metallocene/cocatalyst solution or metallocene/cocatalyst mixture can be added to the support material or the support material can be introduced into the solution.

25 The volume of the preactivated solution or metallocene/cocatalyst mixture can exceed 100% of the total pore volume of the support material used or else can be up to 100% of the total pore volume.

The temperature at which the preactivated solution or

30 metallocene/cocatalyst mixture is brought into contact with the support material can vary in the range from 0 to 100 °C. However, lower or higher temperatures are also possible.

Subsequently, all or most of the solvent is removed from the  
35 supported catalyst system, with the mixture being able to be stirred and also heated if desired. Preference is given to removing both the visible proportion of the solvent and also the proportion in the pores of the support material. The removal of the solvent can be carried out in a conventional way using  
40 reduced pressure and/or flushing with inert gas. In the drying process, the mixture can be heated until the free solvent has been removed, which usually takes from 1 to 3 hours at a preferred temperature of from 30 to 60 °C. The free solvent is the visible proportion of solvent in the mixture. For the purposes of  
45 the present invention, residual solvent is the proportion enclosed in the pores.

As an alternative to complete removal of the solvent, the

supported catalyst system can also be dried only to a certain residual solvent content, with the free solvent having been completely removed. The supported catalyst system can subsequently be washed with a low-boiling hydrocarbon such as pentane or hexane and dried again.

After it has been prepared, the supported catalyst system can either be used directly for the polymerization of olefins or be prepolymerized using one or more olefinic monomers prior to use in a polymerization process. The prepolymerization of supported catalyst systems is described, for example, in WO 94/28034.

As additive, a small amount of an olefin, preferably a  $\alpha$ -olefin (for example styrene or phenyldimethylvinylsilane) as activity-promoting component, or, for example, an antistatic can be added during or after the preparation of the supported catalyst system.

As antistatic, use is customarily made of a mixture of a metal salt of Medialan acid, a metal salt of anthranilic acid and a polyamine. Such antistatics are described, for example, in EP-A-0,636,636.

The molar ratio of additive to metallocene component (compound (I)) is preferably from 1 : 1000 to 1000 : 1, very particularly preferably from 1 : 20 to 20 : 1.

The present invention also provides a process for preparing a polyolefin by polymerization of one or more olefins in the presence of the catalyst system comprising at least one transition metal component of the formula I or II which is obtainable by the purification process of the present invention. For the purposes of the present invention, the term polymerization encompasses both homopolymerization and copolymerization.

The metallocenes of the formulae I and II obtained in the purification process of the present invention display olefin polymerization activities which are at least equal to and sometimes superior to those of the dihalide compounds, and the polyolefins obtained display a reduction in the proportion of undesirable low molecular weight extractables.

The catalyst system described here can be used as sole catalyst component for the polymerization of olefins having from 2 to 20 carbon atoms, but is preferably used in combination with at least one alkyl compound of elements of main group I to III of the



Periodic Table, e.g. an aluminum alkyl, magnesium alkyl or lithium alkyl or an aluminoxane. The alkyl compound is added to the monomers or the suspension medium and serves to free the monomers of substances which can adversely affect the catalyst activity. The amount of alkyl compound added depends on the quality of the monomers used.

As molar mass regulator and/or to increase the activity, hydrogen is added if required.

10

In the polymerization, the antistatic can be introduced into the polymerization system either together with or separately from the catalyst system used.

- 15 The polymers prepared using the catalyst system comprising at least one of the metallocenes of the formulae I and II obtained in the purification process of the present invention display a uniform particle morphology and contain no fines. No deposits or caked material occur in the polymerization using the catalyst system.

The catalyst system gives polymers such as polypropylene with extraordinarily high stereospecificity and regiospecificity.

- 25 The stereospecificity and regiospecificity of polymers, particularly polypropylene, is defined, in particular, by the triad tacticity (TT) and the proportion of 2-1-inserted propene units (RI), which can be determined from the  $^{13}\text{C}$ -NMR spectra.

- 30 The  $^{13}\text{C}$ -NMR spectra are measured in a mixture of hexachlorobutadiene and  $\text{d}_2$ -tetrachloroethane at elevated temperature (365 K). All  $^{13}\text{C}$ -NMR spectra of the polypropylene samples measured are calibrated on the basis of the resonance signal of  $\text{d}_2$ -tetrachloroethane ( $\delta = 73.81$  ppm).

35


To determine the triad tacticity of the polypropylene, the methyl resonance signals in the  $^{13}\text{C}$ -NMR spectrum from 23 to 16 ppm are examined; cf. J. C. Randall, Polymer Sequence Determination: Carbon-13 NMR Method, Academic Press New York 1978; A. Zambelli,

- 40 P. Locatelli, G. Bajo, F. A. Bovey, Macromolecules 8 (1975), 687-689; H. N. Cheng, J. A. Ewen, Makromol. Chem. 190 (1989), 1931-1943. Three successive 1-2-inserted propene units whose methyl groups are on the same side in the "Fischer projection" are referred to as mm triads ( $\delta = 21.0$  ppm to 22.0 ppm). If only the second methyl group of three successive propene units points to the other side, one speaks of an rr triad ( $\delta = 19.5$  ppm to 20.3 ppm) and if only the third methyl group of the three successive

propene units points to the other side, this is referred to as an mr triad ( $\delta = 20.3$  ppm to 21.0 ppm). The triad tacticity is calculated according to the following formula:

$$5 \text{ TT (\%)} = \text{mm} / (\text{mm} + \text{mr} + \text{rr}) \cdot 100$$

If a propene unit is inserted inversely into the growing polymer chain, this is referred to as a 2-1 insertion; cf. T. Tsutsui, N. Ishimaru, A. Mizuno, A. Toyota, N. Kashiwa, Polymer 30, (1989),  
 10 1350-56. The following structural arrangements are possible:



25 The proportion of 2-1-inserted propene units (RI) can be calculated according to the following formula:

$$\text{RI (\%)} = 0.5 \text{ I}_{\alpha, \beta} (\text{I}_{\alpha, \alpha} + \text{I}_{\alpha, \beta} + \text{I}_{\alpha, \delta}) \cdot 100,$$

30 where

$\text{I}_{\alpha, \alpha}$  is the sum of the intensities of the resonance signals at  $\delta = 41.84, 42.92$  and  $46.22$  ppm,

35  $\text{I}_{\alpha, \beta}$  is the sum of the intensities of the resonance signals at  $\delta = 30.13, 32.12, 35.11$  and  $35.57$  ppm

and

40  $\text{I}_{\alpha, \delta}$  is the intensity of the resonance signal at  $\delta = 37.08$  ppm.

The isotactic polypropylene which has been prepared using the catalyst system has a proportion of 2-1-inserted propene units RI of  $< 0.5\%$  at a triad tacticity TT of  $> 98.0\%$  and a melting point  
 45 of  $> 153^\circ\text{C}$ , and the  $M_w/M_n$  of the polypropylene prepared according to the present invention is from 2.5 to 3.5.

The copolymers which can be prepared using the catalyst system have a significantly higher molar mass than those of the prior art. At the same time, the use of the catalyst system enables such copolymers to be prepared with high productivity at industrially relevant process parameters without deposit formation.

The polymers prepared by the process are particularly useful for producing hard and stiff shaped bodies having a high tensile strength, for example fibers, filaments, injection-molded parts, films, sheets or large hollow bodies (e.g. pipes).

The invention is illustrated by the following nonlimiting examples.

15

General procedures: preparation and handling of organometallic compounds was carried out in the absence of air and moisture under argon (Schlenk technique or glove box). All solvents required were purged with argon and dried over molecular sieves before use.

20

Example 1: Dimethylsilanediylbis(2-methyl-4,5-benzoindenyl)zirconium monochloride mono(2,4-di-tert-butylphenoxide) (1)

25

20.6 g (0.1 mol) of 2,4-di-tert-butylphenol in 200 ml of toluene/20 ml of THF were admixed at room temperature with 37.2 ml (0.1 mol) of a 20% strength solution of butyllithium in toluene. The mixture was stirred for another 1 hour at 60°C. At room temperature, 28.8 g (0.05 mol) of dimethylsilanediyl-bis(2-methyl-4,5-benzoindenyl)zirconium dichloride were added as a solid. The suspension was stirred at 100°C for 3 hours and subsequently filtered hot through Celite. The filter cake was extracted 3 times with 100 ml each time of toluene (100°C). After evaporation of the solvent, the yellow solid which had precipitated was filtered off and dried under reduced pressure. This gave 31.1 g (83%) of dimethylsilanediylbis(2-methyl-4,5-benzoindenyl)zirconium monochloride mono(2,4-di-tert-butylphenoxide) (1).

40

<sup>1</sup>H-NMR (400 MHz, CDCl<sub>3</sub>): 8.05 (dd, 1H), 7.75 (m, 2H), 7.65 (dd, 1H), 7.60 (1H), 7.5 - 7.15 (m, 6H), 7.1 (m, 1H), 7.0 (m, 1H), 6.85 (s, 1H), 6.8 (d, 1H), 6.65 (m, 1H), 5.45 (d, 1H), 2.82 (s, 3H), 2.45 (s, 3H), 1.45 (s, 3H), 1.35 (s, 3H), 1.25 (s, 9H), 0.95 (s, 9H).

## Solubility comparison:

50 mg of  
dimethylsilanediylbis(2-methyl-4,5-benzoindenyl)zirconium  
5 dichloride dissolved completely in 240 ml of toluene at room  
temperature (solubility: about 0.36 mmol/l).

50 mg of the compound (1) dissolved immediately in < 5 ml of  
toluene at room temperature (solubility: > 13 mmol/l).

10

Example 1a: Preparation of a catalyst using (1) and  
polymerization:

35.1 mg (0.047 mmol) of (1) were stirred in 2.1 ml of 30%  
15 strength MAO solution in toluene (Al/Zr=215) for 60 minutes at  
room temperature. 2 g of SiO<sub>2</sub> (Grace XPO2107, pretreated at 140°C,  
10 mbar, 10 hours) were subsequently added and the mixture was  
stirred for another 10 minutes. The solvent was removed in an oil  
pump vacuum.

20

A dry 2 l reactor was flushed firstly with nitrogen and  
subsequently with propylene and charged with 1.5 l of liquid  
propylene. 2 ml of TEA (20% strength in Varsol) were added  
thereto and the mixture was stirred for 15 minutes. The catalyst  
25 system prepared above (0.886 g) was subsequently resuspended in  
20 ml of heptane and then injected into the reactor and rinsed in  
with 15 ml of heptane. The reaction mixture was heated to the  
polymerization temperature of 60°C and polymerization was carried  
out for 1 hour. The polymerization was stopped by venting the  
30 remaining propylene. The polymer was dried in a vacuum drying  
oven. This gave 470 g of polypropylene powder. The reactor  
displayed no deposits on the inner wall or stirrer. The catalyst  
activity was 0.53 kg of PP/g of catalyst x h.

35 Comparative example:

Preparation of a catalyst using  
dimethylsilanediylbis(2-methyl-4,5-benzoindenyl)zirconium  
dichloride and polymerization

40

27.1 mg (0.047 mmol) of  
dimethylsilanediylbis(2-methyl-4,5-benzoindenyl)zirconium  
dichloride were stirred in 2.1 ml of 30% strength MAO solution in  
toluene (Al/Zr=215) for 60 minutes at room temperature. 2 g of  
45 SiO<sub>2</sub> (Grace XPO2107, pretreated at 140°C, 10 mbar, 10 hours) were

subsequently added and the mixture was stirred for another 10 minutes. The solvent was removed in an oil pump vacuum.

A dry 2 l reactor was flushed firstly with nitrogen and subsequently with propylene and charged with 1.5 l of liquid propylene. 2 ml of TEA (20% strength in Varsol) were added thereto and the mixture was stirred for 15 minutes. The catalyst system prepared above (0.897 g) was subsequently resuspended in 20 ml of heptane and then injected into the reactor and rinsed in with 15 ml of heptane. The reaction mixture was heated to the polymerization temperature of 60°C and polymerization was carried out for 1 hour. The polymerization was stopped by venting the remaining propylene. The polymer was dried in a vacuum drying oven. This gave 410 g of polypropylene powder. The reactor displayed no deposits on the inner wall or stirrer. The catalyst activity was 0.46 kg of PP/g of catalyst x h.

Example 2: Dimethylsilanediyl-bis(2-methylindenyl)zirconium monochloride mono(2,4-di-tert-butylphenoxide) (2)

1.03 g (5 mmol) of 2,4-di-tert-butylphenol in 10 ml of toluene/1 ml of THF were admixed at room temperature with 1.85 ml (5 mmol) of a 20% strength solution of butyllithium in toluene. The mixture was stirred for another 1 hour at 60°C. At room temperature, 1.19 g (2.5 mmol) of dimethylsilanediyl-bis(2-methylindenyl)zirconium dichloride were added as a solid. The suspension was stirred at 60°C for 2 hours and subsequently filtered hot through Celite. The filter cake was extracted 3 times with 10 ml each time of toluene (60°C). After evaporation of the solvent, the yellow solid which had precipitated was filtered off and dried under reduced pressure. This gave 0.87 g (53%) of dimethylsilanediylbis(2-methylindenyl)zirconium monochloride mono(2,4-di-tert-butylphenoxide) (2).

<sup>1</sup>H-NMR (400 MHz, CDCl<sub>3</sub>): 8.03 (dd, 1H), 7.6 (dd, 1H), 7.25 - 7.2 (m, 2H), 7.15 (m, 1H), 7.1-7.0 (m, 2H), 6.9 (m, 1H), 6.8 (s, 1H), 6.75 (m, 1H), 6.7 (m, 1H), 6.3 (s, 1H), 5.55 (d, 1H), 2.65 (s, 3H), 2.3 (s, 3H), 1.3 (s, 3H), 1.25 (s, 9H), 1.22 (s, 3H), 1.15 (s, 9H).

Solubility comparison:

50 mg of dimethylsilanediylbis(2-methylindenyl)zirconium dichloride dissolved completely in 50 ml of toluene at room temperature (solubility: about 2.1 mmol/l).

50 mg of the compound (2) dissolved immediately in < 5 ml of toluene at room temperature (solubility: > 15 mmol/l).

Example 3: Dimethylsilanediylbis(2-methyl-4,5-benzoindenyl)zirconium monochloride mono(2-isopropyl-5-methylphenoxide) (3)

2.7 g (17.4 mmol) of 2-isopropyl-5-methylphenol in 20 ml of toluene/2 ml of THF were admixed at room temperature with 6.5 ml (17.4 mmol) of a 20% strength solution of butyllithium in toluene. The mixture was stirred for another 1 hour at 60°C. At room temperature, 5.0 g (8.7 mmol) of dimethylsilanediylbis(2-methyl-4,5-benzoindenyl)zirconium dichloride were added as a solid. The suspension was stirred at 100°C for 4 hours and subsequently filtered hot through Celite. The filter cake was extracted twice with 25 ml each time of toluene (100°C). After evaporation of the solvent, the yellow solid which had precipitated was filtered off and dried under reduced pressure. This gave 2.5 g (41%) of dimethylsilanediylbis(2-methyl-4,5-benzoindenyl)zirconium monochloride mono(2-isopropyl-5-methylphenoxide) (3).

<sup>1</sup>H-NMR (400 MHz, CDCl<sub>3</sub>): 7.9 (dd, 1H), 7.81 (m, 1H), 7.74 (m, 1H), 7.54 (m, 2H), 7.45 - 7.08 (m, 8H), 6.65 (d, 1H), 6.55 (s, 1H), 6.35 (m, 1H), 5.56 (d, 1H), 2.58 (s, 3H), 2.35 (s, 3H), 2.3 (m, 1H), 2.1 (s, 3H), 1.37 (s, 3H), 1.27 (s, 3H), 0.75 (d, 3H), 0.62 (d, 3H).

Solubility comparison:

50 mg of dimethylsilanediylbis(2-methyl-4,5-benzoindenyl)zirconium dichloride dissolved completely in 240 ml of toluene at room temperature (solubility: about 0.36 mmol/l).

50 mg of the compound (3) dissolved in 4 ml of toluene at room temperature (solubility: about 18 mmol/l).

Example 4: Dimethylsilanediylbis(2-methylindenyl)zirconium monochloride mono(2-isopropyl-5-methylphenoxide) (4)

3.2 g (21 mmol) of 2-isopropyl-5-methylphenol in 20 ml of toluene/2 ml of THF were admixed at room temperature with 7.8 ml (21 mmol) of a 20% strength solution of butyllithium in toluene. The mixture was stirred for another 1 hour at 60°C. At room temperature, 5.0 g (10.5 mmol) of dimethylsilanediylbis(2-methylindenyl)zirconium dichloride were

added as a solid. The suspension was stirred at 100°C for 2 hours and subsequently filtered hot through Celite. The filter cake was extracted twice with 25 ml each time of toluene (100°C). After evaporation of the solvent, the yellow solid which had

- 5 precipitated was filtered off and dried under reduced pressure. This gave 1.36 g (22%) of dimethylsilanediylbis(2-methylindenyl)zirconium monochloride mono(2-isopropyl-5-methylphenoxide) (4).

- 10 <sup>1</sup>H-NMR (400 MHz, CDCl<sub>3</sub>): 8.0 (m, 1H), 7.81 (m, 1H), 7.3 - 6.8 (m, 8H), 6.55 (dm, 1H), 6.1 (s, 1H), 5.9 (d, 1H), 2.7 (hept, 1H), 2.45 (s, 3H), 2.25 (s, 3H), 2.18 (s, 3H), 1.4 (s, 3H), 1.25 (s, 3H), 1.1 (d, 3H), 0.95 (d, 3H).

15 Solubility comparison:

50 mg of dimethylsilanediylbis(2-methylindenyl)zirconium dichloride dissolved completely in 50 ml of toluene at room temperature (solubility: about 2.1 mmol/l).

20

50 mg of the compound (4) dissolved in 5 ml of toluene at room temperature (solubility: about 17 mmol/l).

- Example 5: Dimethylsilanediylbis(2-methylindenyl)zirconium monochloride mono(2,4-dimethylphenoxide) (5)
- 25

- 1.0 g (8.2 mmol) of 2,4-dimethylphenol in 20 ml of toluene/2 ml of THF were admixed at room temperature with 3.0 ml (8.2 mmol) of a 20% strength solution of butyllithium in toluene. The mixture was stirred for another 1 hour at 60°C. At room temperature, 1.9 g (4.0 mmol) of dimethylsilanediylbis(2-methylindenyl)zirconium dichloride were added as a solid. The suspension was stirred at 60°C for 8 hours and subsequently filtered hot through Celite. After evaporation of the solvent to about 7 ml, the yellow solid which had precipitated at -30°C was filtered off and dried under reduced pressure. This gave 0.65 g (29%) of dimethylsilanediylbis(2-methylindenyl)zirconium monochloride mono(2,4-dimethylphenoxide) (5).
- 30
- 35

- 40 <sup>1</sup>H-NMR (400 MHz, CDCl<sub>3</sub>): 7.96 (dd, 1H), 7.6 (m, 1H), 7.36 (m, 1H), 7.31 (m, 1H), 7.29 (d, 1H), 7.1 (m, 1H), 6.99 (m, 1H), 6.94 (m, 1H), 6.88 (s, 1H), 6.75 (m, 1H), 6.65 (m, 1H), 6.06 (s, 1H), 5.93 (d, 1H), 2.4 (s, 3H), 2.24 (s, 3H), 2.18 (s, 3H), 1.85 (s, 3H), 1.35 (s, 3H), 1.24 (s, 3H).

45

## 40

Example 6: Dimethylsilanediylbis(2-methyl-4,5-benzoindenyl)-zirconium monochloride mono(2,4-di-tert-pentylphenoxide) (6)

- 5 0.85 g (3.5 mmol) of 2,4-di-tert-pentylphenol in 10 ml of toluene/1 ml of THF were admixed at room temperature with 1.3 ml (3.5 mmol) of a 20% strength solution of butyllithium in toluene. The mixture was stirred for another 1 hour at 60°C. At room temperature, 1.0 g (1.74 mmol) of dimethylsilanediylbis(2-methyl-
- 10 4,5-benzoindenyl)zirconium dichloride were added as a solid. The suspension was stirred at 100°C for 4 hours, diluted with 40 ml of toluene and subsequently filtered hot through Celite. The filter cake was extracted twice with 25 ml each time of toluene (100°C). After evaporation of the solvent to 10 ml, the yellow solid which
- 15 had precipitated was filtered off, washed with a little cold toluene and dried under reduced pressure. This gave 0.85 g (63%) of dimethylsilanediylbis(2-methyl-4,5-benzoindenyl)zirconium monochloride mono(2,4-di-tert-pentylphenoxide) (6).
- 20 <sup>1</sup>H-NMR (400 MHz, CDCl<sub>3</sub>): 8.00 (d, 1H), 7.74 (t, 2H), 7.64-7.57 (m, 2H), 7.45 - 7.27 (m, 5H), 7.14 (s, 1H), 7.10 (m, 1H), 6.98 (m, 1H), 6.78 (s, 1H), 6.65 (d, 1H), 6.52 (dd, 1H), 5.38 (d, 1H), 2.78 (s, 3H), 2.41 (s, 3H), 1.46 (quart., 2H), 1.41 (s, 3H), 1.30 (s, 3H), 1.22 (m, 2H), 1.14 (s, 3H), 1.13 (s, 3H), 0.91 (s,
- 25 3H), 0.88 (s, 3H), 0.57 (t, 3H), 0.39 (t, 3H).

Solubility comparison:

- 50 mg of dimethylsilanediylbis(2-methyl-
- 30 4,5-benzoindenyl)zirconium dichloride dissolved completely in 240 ml of toluene at room temperature (solubility: about 0.36 mmol/l).
- 55 mg of the compound (6) dissolved in 4 ml of toluene at room
- 35 temperature (solubility: about 17.7 mmol/l).